



College of Art and Design

Image Permanence Institute

PHOTOGRAPHIC ACTIVITY TEST ISO 18916 - RESEARCH REPORT

Job 2635

DATE: 2-May-2022

PREPARED FOR: Anja Spitzer - Neschen Coating GmbH
 Hans-Neschen-Straße 1, 31675 Bückeburg, Germany

MATERIAL: Gudy DS 12

CONTROL: Whatman No. 1 filter paper

SILVER IMAGE INTERACTION	RESULT: PASS
---------------------------------	---------------------

Density change of control:	-1.01	Percentage
Upper pass/fail limit:	-0.81	-20%
Density change of material:	-0.96	-5%
Lower pass/fail limit:	-1.21	20%

Density change caused by material must be equal to density change caused by control $\pm 20\%$

GELATIN STAINING	RESULT: PASS
-------------------------	---------------------

Density change of control:	0.12
Stain limit:	0.20
Density change of material:	0.12

Stain caused by material must be less than stain caused by control ± 0.08

MOTTLING OF IMAGE INTERACTION DETECTOR	RESULT: PASS
---	---------------------

Visual assessment of uniform action

OPERATOR: Meredith Noyes

PAT PERFORMANCE:	PASS
-------------------------	-------------

MUST PASS ALL CRITERIA TO PASS PAT

Note: When selecting enclosures, the PAT should be used in conjunction with ISO 18902.

This certificate is valid for this specific lot of product until any date and for subsequent lots until: **2-May-2023**

This certificate is VOID upon any change in product formulation, manufacturer, or manufacturer supplier.