



Instructions for mixing the dry resins for Beva 371.

In a heated water bath (double boiler) add contents of package A, and add 1000g Toluene, and 250g Benzine (naphtha). Stir until dissolved.

In a separate heated water bath (double boiler) add contents of package B, and add 550g Benzine (naphtha), and stir until dissolved. Then pour contents of B into A and stir well together, slowly let cool in the double boiler until the water is cool.

P.S. For the parts to be completely dissolved, each solution when dissolved separately, and then both together, must be above the cloud point, i.e. clear with no lumps.